

AMENDMENTS TO THE CLAIMS

1-13. (Cancelled)

14. (Previously presented) A process for the manufacture of a polystyrene closed-cell foam in which a blowing agent comprising 1,1-difluoroethane, 1,1,1,2-tetrafluoroethane and optionally an additive is employed.

15. (Previously presented) The process according to Claim 14, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is at least 1.5.

16. (Previously presented) The process according to Claim 15, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is more than 2.

17. (Previously presented) The process according to Claim 14, in which the blowing agent contains more than 60% by weight of a mixture of 1,1-difluoroethane and 1,1,1,2-tetrafluoroethane.

18. (Previously presented) The process according to Claim 14, wherein said additive is alcohol.

19. (Previously presented) A composition comprising 1,1-difluoroethane and 1,1,1,2-tetrafluoroethane and an alcohol, which composition can be used as blowing agent for the manufacture of polymer-based foams.

20. (Previously presented) The composition according to Claim 19, wherein said alcohol is methanol, ethanol, n-propanol or isopropanol.

Application No.: 10/070979

Docket No.: 05129-00053-US

21. (Previously presented) A composition comprising 1,1-difluoroethane, 1,1,1,2-tetrafluoroethane and carbon dioxide, wherein the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is greater than 1, which can be used as blowing agent for the manufacture of polymer-based foam.
22. (Previously presented) The composition according to Claim 19, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane is at least 1.5.
23. (Previously presented) The composition according to Claim 19, containing more than 60% by weight of 1,1-difluoroethane and of 1,1,1,2-tetrafluoroethane.
24. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 14.
25. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 16.
26. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 17.
27. (Previously presented) The process according to Claim 14, wherein the polystyrene closed-cell foam contains more than 90% of closed cells.
28. (Previously presented) The process according to Claim 27, wherein the thermal conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.

Application No.: 10/070979

Docket No.: 05129-00053-US

29. (Previously presented) The thermal insulation panel according to Claim 24, wherein the polystyrene closed-cell foam contains more than 90% of closed cells.
30. (Previously presented) The thermal insulation panel according to Claim 24, wherein the thermal conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.
31. (Previously presented) The thermal insulation panel according to Claim 29, wherein the thermal conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.
32. (New) The composition according to Claim 21, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane is at least 1.5.
33. (New) The composition according to Claim 21, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane is at least 2.3.
34. (New) The composition according to Claim 21, containing more than 60% by weight of 1,1-difluoroethane and of 1,1,1,2-tetrafluoroethane.

Application No.: 10/070979

Docket No.: 05129-00053-US

AMENDMENTS TO THE CLAIMS

1-13. (Cancelled)

14. (Previously presented) A process for the manufacture of a polystyrene closed-cell foam in which a blowing agent comprising 1,1-difluoroethane, 1,1,1,2-tetrafluoroethane and optionally an additive is employed.
15. (Previously presented) The process according to Claim 14, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is at least 1.5.
16. (Previously presented) The process according to Claim 15, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is more than 2.
17. (Previously presented) The process according to Claim 14, in which the blowing agent contains more than 60% by weight of a mixture of 1,1-difluoroethane and 1,1,1,2-tetrafluoroethane.
18. (Previously presented) The process according to Claim 14, wherein said additive is alcohol.
19. (Previously presented) A composition comprising 1,1-difluoroethane and 1,1,1,2-tetrafluoroethane and an alcohol, which composition can be used as blowing agent for the manufacture of polymer-based foams.
20. (Previously presented) The composition according to Claim 19, wherein said alcohol is methanol, ethanol, n-propanol or isopropanol.

362188_1

Application No.: 10/070979

Docket No.: 05129-00053-US

21. (Previously presented) A composition comprising 1,1-difluoroethane, 1,1,1,2-tetrafluoroethane and carbon dioxide, wherein the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane in the blowing agent is greater than 1, which can be used as blowing agent for the manufacture of polymer-based foam.
22. (Previously presented) The composition according to Claim 19, in which the weight ratio of 1,1-difluoroethane to 1,1,1,2-tetrafluoroethane is at least 1.5.
23. (Previously presented) The composition according to Claim 19, containing more than 60% by weight of 1,1-difluoroethane and of 1,1,1,2-tetrafluoroethane.
24. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 14.
25. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 16.
26. (Previously presented) A thermal insulation panel comprising the polystyrene closed-cell foam, obtained using the process according to Claim 17.
27. (Previously presented) The process according to Claim 14, wherein the polystyrene closed-cell foam contains more than 90% of closed cells.
28. (Currently amended) The process according to Claim 27, wherein the thermal conductivity at 10° conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.

Application No.: 10/070979

Docket No.: 05129-00053-US

29. (Previously presented) The thermal insulation panel according to Claim 24, wherein the polystyrene closed-cell foam contains more than 90% of closed cells.
30. (Currently amended) The thermal insulation panel according to Claim 24, wherein the thermal ~~conductivity at 10°~~ conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.
31. (Currently amended) The thermal insulation panel according to Claim 29, wherein the thermal ~~conductivity at 10°~~ conductivity at 10°C of the polystyrene closed-cell foam after 90 days storage at room temperature is 27.0 mW/m.K or less.